

Technical Data Sheet

# 23µm STANDARD

## LLDPE500/23

TYP  
Quality

Characteristics	Unit	Values *
[µm]		<b>23 ± 5%</b>
Thickness		
[g/cm <sup>3</sup> ]		<b>0,918</b>
Density		
[%]		<b>150 ± 10%</b>
Pre-stretchGuaranteed (Quality Test Plot)		
[%]		<b>&lt; 355</b>
Elongationatbrake (Ultimate Test Plot)		
[kg]		<b>1,58 ± 10%</b>
Puncture test		
[kg]		<b>1,65 ± 10%</b>
Retention Maximum Force		
[kg]		<b>1,38 ± 10%</b>
RetentionForce		
[g]		<b>31,5 ± 10%</b>
Cling		
[dB]		<b>79,80</b>

### Soundlevel

\* The given parameters values were established on the basis of laboratory tests conveyed in specific conditions. In case the manufacturer's recommendations are disobeyed, especially in regard to storage and usage conditions, those parameters may differ from the values assumed in Technical Data Sheet.

*External view of the product: T **transparent film without discoloration, tearing, holes, without pressed folds.***

*We hereby certify that this product does not put in danger the life, health, working security and environmental protection and is in conformity with the standards : ASTM D-882, ASTM D-1922, ASTM D-1709. In accordance with the applicable regulation stretch film is not classified as a dangerous product. It does not contain dangerous substances in conformity with EN- 13428 norm and heavy metals, phthalates, chlorine, Bisphenol A i S, mineral oil, tin, tantalum, tungsten, gold. **The film contains no plasticizers.** Has a certified quality management system ISO 9001, which contains the requirements of Good Manufacturing Practice GMP and certified environmental management system ISO 14001. **Storage conditions:** temperature range +10°C do +25°C, moisture 40%- 70%, no direct sunlight or rain falls, no smoking, no open flames or sources of ignition in the storage area. **Handling:** application temperature range -5°C do +30°C regarding seasonality and cling properties.*